



23 Exhibition Drive, Malaga Western Australia

Monday - Friday 7am-5pm + Sat 8am-4pm

Sales Centre for Sales, Advice + Orders

T +61 8 9209 7400

hello@beyondtools.com

3.785L TITEBOND III ULTIMATE WOOD GLUE



| SKU | Option | Part # | Price |
|-------|--------|--------|----------|
| 54365 | | 511416 | \$105.95 |

| Model | |
|-----------------------------|--------------|
| Type | Wood Glue |
| SKU | 54365 |
| Part Number | 511416 |
| Barcode | 037083014167 |
| Brand | Titebond |
| Size | 3.785L |
| Dimensions | |
| Product Weight (Net Weight) | 4.44 kg |
| Packaging + Shipping | |
| Shipping Weight (Gross) | 4.3 kg |

Titebond III Ultimate is the most advanced wood glue available today. While all Titebond products provide superior performance, Titebond III is especially useful for outdoor applications in cooler temperatures or when concern for substantial moisture calls for the use of a Type I glue (USA boil test). For interior applications, the longer working time of Titebond III provides woodworkers the necessary latitude to ensure that substrates are precisely aligned before being bonded. Overall, Titebond III combines superior strength, sandability with water cleanup the ease of use of aliphatic resins with the, durability and water resistance of polyurethanes into one easy-to-use formulation. **Features:-**

Passes ANSI/HPVA Type I water-resistance and D3 european standard (passes the USA boil test)

Waterproof formula that cleans up with water

Superior strength “ Strong initial tack (has the highest bond strength of the cross link PVA)

Designed for interior and exterior applications

Longer open assembly time

Lower application temperature

Unaffected by finishes

FDA approved for indirect food contact

Physical Properties:-

Type Advanced Proprietary Polymer

State Liquid

Colour Tan

Dried film Light Brown

Solids 52%

Viscosity 4,200 cps

Storage life 24 months in tightly closed containers below 24 °C

Calculated VOC 9 g/L



23 Exhibition Drive, Malaga Western Australia

Monday - Friday 7am-5pm + Sat 8am-4pm

Sales Centre for Sales, Advice + Orders

T +61 8 9209 7400

hello@beyondtools.com

| | |
|-----------------------|--------------------|
| Weight per gallon | 4.17kg |
| Chalk temperature | Approximately 7 °C |
| Flashpoint | > 93 °C |
| Freeze/thaw stability | Stable |
| pH | 2.5 |

Application Guidelines:-

Application Temperature Above 8.33 °C.

Open Assembly Time 8-10 minutes (21.1 °C./50%RH)

Total Assembly Time 20-25minutes (21.1 °C./50%RH)

Minimum Required Spread Approximately 6.18 square meters per litre

Required Clamping Pressure Enough to bring joints tightly together (generally, 100-150 psi for softwoods, 125-175 psi for medium woods and 175-250 psi for hardwoods)

Method of Application Plastic bottles for fine applications; glue may also be spread with a roller spreader or brush.

Cleanup Damp cloth while glue is wet. Scrape off and sand dried excess.

Limitations:- Not for continuous submersion or for use below the waterline. Not for structural or load bearing applications. Use when temperature, glue and materials are above 7.22 °C. Store product below 23.8 °C. Storage above this temperature may cause product to thicken and reduce the usable shelf life. If thickened, shake vigorously by firmly tapping bottle on a hard surface until product is restored to original form. Because of variances in the surfaces of treated lumber, it is a good idea to test for adhesion. For best results gluing exterior doors or exotic and oily woods, please contact our Technical Support Team at 1-800-347-4583. Read MSDS before use. KEEP FROM FREEZING. **KEEP OUT OF THE REACH OF CHILDREN.**

Material Data Specifications:-

MSDS

Data Sheet