



23 Exhibition Drive, Malaga Western Australia

Monday - Friday 7am-5pm + Sat 8am-4pm

Sales Centre for Sales, Advice + Orders

T +61 8 9209 7400

[hello@beyondtools.com](mailto:hello@beyondtools.com)

## 237ML QUICK & THICK 512403 BY TITEBOND



SKU	Option	Part #	Price
9803365		512403	\$16.9

Model	
Type	PVA
SKU	9803365
Part Number	512403
Barcode	037083024036
Brand	Titebond
Size	237ml
Technical - Main	
Colour Name	White
Dimensions	
Product Weight (Net Weight)	0.27 kg
Packaging + Shipping	
Shipping Weight (Gross)	0.4 kg

Titebond Quick & Thick Multi-Surface Glue is the thickest, fastest-drying water-based glue available for use with porous and semi-porous materials. It is ideal for wood, pottery, ceramic, stone, glass, fabrics, leather and most craft-type materials. Titebond Quick & Thick Multi-Surface Glue provides a strong initial tack and fast speed of set, yet allows realignment of working pieces. It also develops a bond stronger than the wood itself, dries clear and is unaffected by finishes. **Features:-**

2X Faster & 3X Thicker than traditional PVA glues

Dries clear & Paintable

Ideal for the woodshop, home and craft projects

Fill small cracks and gaps

Unaffected by finishes

Excellent sandability on wood

Designed for interior projects

Water cleanup & non-toxic

Nonflammable & No offensive odor

Conforms to ASTM D4236

### Physical Properties:-

Type Thixotropic polyvinyl acetate

State High-viscosity liquid

Colour White

Dried film Clear

Solids 60%

Viscosity 36,500 cps

Storage life 24 months in tightly closed containers at 24 °C

Calculated VOC 2.4g/L

Weight per gallon 4.08kg

Chalk temperature Approximately 10 °C



**23 Exhibition Drive, Malaga Western Australia**

Monday - Friday 7am-5pm + Sat 8am-4pm

**Sales Centre** for Sales, Advice + Orders

T +61 8 9209 7400

[hello@beyondtools.com](mailto:hello@beyondtools.com)

Flashpoint > 93 °C  
Freeze/thaw stability Stable up to 2 cycles  
pH 4.8

**Application Guidelines:- Application Temperature**

Above 10 °C. **Open Assembly Time** 3-5 minutes (21

°C./50%RH) **Total Assembly Time** 10-15 minutes (21

°C./50%RH) **Minimum Required Spread** Approximately 6

square meters per litre **Required Clamping Pressure**

Enough to bring joints tightly together (generally, 100-150

psi for soft woods, 125-175 psi for medium woods and 175-

250 psi for hardwoods) **Method of Application** Plastic

bottles for fine applications; glue may also be spread with a

roller, spreader or brush. **Cleanup** Damp cloth while glue is

wet. Scrape off and sand dried excess. **Technical Data:-**

Download MSDS Here.

Download Data Sheet Here.